

Product composition

Carrier: MDF 18 mm
Chipboard 18 mm

	Look	Top layer thickness	Dimensions	Jointing method	Cutting method
Natura	Adagio	0,6 / 1 / 1,5 mm	2500x1240 mm (US: 2500x1250 or 8' x 4')	Mixmatch	Quarter cut
	Allegro		3050x1220 mm (US: 3060x1250 or 10' x 4')		Quarter cut Half-crown cut
	Vivace		2800x2070 mm (US: 9'x6,5')		Quarter cut Crown cut Half-crown cut
	Adagio Infinite	0,6 mm	3050x1220 mm (US: 3060x1250 or 10' x 4')	Slipmatch	Quarter cut
	Allegro Infinite	0,6 mm		Mixmatch	Quarter cut Half-crown cut
	Animato Infinite	0,6 mm		Slipmatch	Full crown cut
Terra	Crema	0,6 mm	3050x1220 mm (US: 3060x1250 or 10' x 4')	Mixmat ch	Quarter cut (Half-)Crown cut
	Macchiato	0,6 mm			
	Latte	0,6 mm			
	Grigio	0,6 mm			
	Cammello	0,6 mm			
	Mocha	0,6 mm			
	Topo	0,6 mm			
	Tartufo	0,6 mm			
	Espresso	0,6 mm			
Vintage	Harlem	1	2500x1240 mm (US: 2500x1250 or 8' x 4') 3050x1220 mm (US: 3060x1250 or 10' x 4')		Not specified
	Hoboken	1			
	Baltimore	1			

Thickness tolerances carriers

MDF carrier thickness 18mm: +-0.20 mm Chipboard carrier thickness 18 mm: +-0.3 mm

Thickness tolerances veneersheet

0.6 mm +-0.1 mm / 1 mm +- 0.2 mm / 1.5 mm +- 0.35 mm

Finishing Advice (see also seperate sheet)

Querkus panels are only presanded. Querkus panels are not treated and can be finished according to own taste.

Dyed oak varies in color when exposed to sunlight. We strongly advice to finish the panels with a varnish or oil that contains UV-blocking components.

Querkus quality sheet panels

QUERKUS[®]

FINEST OAK
COLLECTION

Exclusive quality: Querkus veneer with chosen look, thickness and touch.

Select quality: For applications where the backside of the panel is occasionally visible.

Basic quality: For applications where the backside of the panel is not visible.

This quality is only available for Adagio, Allegro and Vivace.

		Exclusive	Select	Basic
	Subcollection	Front- and backside	Front: see Exclusive Backside:	Front: see Exclusive Backside:
View	All	Same as chosen top layer	Natural oak - jointing not specified	Natural oak - jointing not specified
Flake size	All	Small flake	Large flake	Large flake
Loose flake	All	Not allowed	Not allowed	Very limited
Colour variations	Natura	Homogeneous with natural variation	Not specified	Not specified
	Terra	Slight color variation	Slight color variation and faded spots or veins	n/a
	Vintage	Natural variation with same undertone	Natural variation with same undertone	n/a
Sapwood	All	Not allowed	Not allowed	Very limited
Jointing method	All	See product composition	Not specified	Not specified
Mineral	Natura	Very limited allowed	Limited allowed	Allowed
	Terra	Very limited allowed	Limited allowed	n/a
	Vintage	Allowed	Allowed	n/a
Worm holes	Natura	Not allowed	Allowed when unobtrusive	Allowed
	Terra	Not allowed	Allowed when unobtrusive	n/a
	Vintage	Allowed	Allowed	n/a
Open defects	Natura	Allowed when unobtrusive	Very limited allowed	Limited allowed
	Terra	Allowed when unobtrusive	Very limited allowed	n/a
	Vintage	Allowed	Allowed	n/a
Wood filler*	Natura	0,6/1 mm: not filled* 1,5 mm: filled	0,6/1 mm: not filled 1,5 mm: filled	0,6/1 mm: not filled 1,5 mm: filled
	Terra	filled	filled	filled
	Vintage	not filled	not filled	n/a
Open joints	All	0,6/1 mm: not allowed 1,5 mm: filled allowed	0,6/1 mm: limited allowed 1,5 mm: filled allowed	Allowed

* This also applies for open knots on the Vivace 0,6 mm and 1 mm

Querkus quality sheet panels

QUERKUS®

FINEST OAK
COLLECTION

Natura Adagio



Natura Allegro



QUERKUS®

FINEST OAK
COLLECTION

Natura Vivace



SELECT backside

Backside Natura Select



QUERKUS®

FINEST OAK
COLLECTION

Backside Vivace A/B+



QUERKUS®

FINEST OAK
COLLECTION

BASIC backside

Backside Natura Adagio/Allegro Basic (A/B)



Backside Natura Vivace (A/B)




QUERKUS®

FINEST OAK
COLLECTION

Crema



Macchiato



Latte



QUERKUS®

FINEST OAK
COLLECTION

Grigio



Cammello



Mocha



QUERKUS®

FINEST OAK
COLLECTION



Tartufo



Espresso



Querkus quality sheet panels

Vintage Harlem

**QUERKUS®**FINEST OAK
COLLECTION

Vintage Hoboken



Vintage Baltimore

**Querkus quality sheet panels**

Unlike other veneers, many characteristics of old oak panels are acceptable and just desired. These open defects are part of the reclaiming look. These include skewer, open knots, cracks, open joints, cutting errors & cracks, missing veneer, dark discoloration, wormholes, open flake.

On the basis of a few pictures this quickly becomes clear. Below is an example of several defects that are allowed within these references.



However, the following items are blatant and no longer decorative and therefore not permitted.

